

Result: Histogram Report

User Name: Jacinta Parenzee

Security Level: 1

Sample Details

Sample ID: 166
 Sample File: ORLA
 Sample Path: C:\SIZERS\DATA\CONTRACT\
 Sample Notes: Upper Steel, tomo fill

Run Number: 4
 Record Number: 34

Measured: Mon 6 Aug 2007 10:19a.m.
 Analysed: Mon 6 Aug 2007 10:19a.m.
 Result Source: Analysed

System Details

Range Lens: 300RF mm
 Presentation: 3OHD
 Analysis Model: Polydisperse
 Modifications: None

Beam Length: 2.40 mm
 [Particle R.I. = (1.5295, 0.1000); Dispersant R.I. = 1.3300]

Sampler: MS17

Obscuration: 19.7 %

Residual: 2.652 %

Result Statistics

Distribution Type: Volume
 Mean Diameters:
 D [4, 3] = 17.94 um

Concentration = 0.0136 %Vol
 D (v, 0.1) = 1.68 um
 D [3, 2] = 4.29 um

Density = 2.560 g / cub. cm
 D (v, 0.5) = 10.62 um
 Span = 4.134E+00

Specific S.A. = 0.5467 sq. m / g
 D (v, 0.9) = 45.60 um
 Uniformity = 1.274E+00

Size (um)	Volume In %	Size (um)	Volume In %	Size (um)	Volume In %	Size (um)	Volume In %
0.050	0.00	3.90	16.90	74.00	1.23	300.0	0.00
0.060	0.00	7.80	18.19	88.00	0.44	350.0	0.00
0.120	0.00	15.60	19.35	105.0	0.00	420.0	0.00
0.240	0.71	31.00	5.00	125.0	0.00	500.0	0.00
0.490	1.83	37.00	4.58	149.0	0.00	590.0	0.00
0.700	2.10	44.00	4.25	177.0	0.00	710.0	0.00
0.980	7.83	53.00	3.02	210.0	0.00	840.0	0.00
2.00	12.64	63.00	1.94	250.0	0.00	1000.0	0.00
3.90		74.00		300.0	0.00	2000.0	0.00

